

LAFAC

ÁRIDOS Y CEMENTOS



Glue cement C1T

Product codes:

Reference: 910

Apparent density: 1,4 g/cm³

Mixing water (+/- 1): 25,00%

Granulometry: < 0,6 mm

Detachment on vertical wall: ≤ 0,5 mm

Open time after 30 m.: 20 min.

Use time: 120 min.

Adherence: ≥ 0,5 N/mm²

Placement of tiles, ceramics, stoneware, baseboards, etc. in small, medium and large sizes. Placement on interior supports. (* see table of coatings).

PRESENTATION

25 kg bags (approx.)

Pallets 40 bags

USES AND APPLICATIONS



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat

LAFAC
ÁRIDOS Y CEMENTOS



Placement of tiles, ceramics, stoneware, baseboards, etc. in small, medium and large sizes. Placement on interior supports. (* see table of coatings).

APPLICATION METHOD

Add between 25 % and 28 % of water and knead it well until obtaining a homogeneous paste. Wait a minimum of 10 minutes. Apply with a trowel.

The support must be completely set and clean. It must be resistant and have a plane with differences of less than 5 mm. Check with a 2 m ruler. of length.

Do not use at temperatures above 30 °C or below 5 °C

RECOMMENDED COATINGS

HANDLING

DRY PRODUCT:

Keep out of the reach of children. Avoid contact with eyes and skin.

Avoid inhalation

PREVENTION

In case of projection of the product dry, on eyes or skin, wash vigorously and go to a healthcare center.



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat





Wear appropriate gloves during application. To avoid dust and splashes it is appropriate to wear safety glasses.

PERFORMANCE

Simple gluing: 4.5 (+/- 0.5) kg / m² (10 mm. Maximum thickness)

Double gluing: 7.5 (+/- 0.5) kg / m² (10 mm. Maximum thickness)

STORAGE

The product should be stored under cover in a clean, dry and well-ventilated place. Non-flammable product.

Consume preferably within 12 months from the date of packaging.



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat

