



Mortar M-2,5 dry

Product codes:

Reference: 804

Apparent density: $> 1,3 \text{ g/cm}^3$

Compression resistance according to type: $> 2,5 \text{ N/mm}^2$

Reaction to fire: Clase A1

Water absorption by capillarity: No disponible

Chloride content: No disponible

Water vapor permeability: $\mu 15/25$

Thermal conductivity: $0,67 \text{ W/mK}$

Durability: Benefit not determined and not declared

Dosage: 1:8

Dry mortar manufactured according to Standard 998-2 (Masonry Mortars) designed for use in general masonry work, both indoors and outdoors.

Manufactured with Type I / 42.5 R cement, limestone aggregates and inorganic additives.

TYPES



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat

LAFAC
ÁRIDOS Y CEMENTOS



M-2,5 Gray

M-2.5 with Cal

PRESENTATION

25 kg bags (approx.)

Pallets 56 bags

Big Bags 1 Tm

USES AND APPLICATIONS

Brick factories

Pavement filling.

Laying of tiles.

And all kinds of masonry work that does not require high resistance.

PREPARATION

The mortar type M-2.5 packed in bags is prepared in a concrete mixer. Add 3.2 liters of water for each bag of mortar (0.125 liters / kg). Depending on the application, it can be up to 3.5 liters (0.14 liters / kg of mortar)

The support must be clean and damp. Do not apply to paint, plaster or breakable



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat





surfaces.

Spread the paste on the support or piece with the help of a trowel or trowel depending on the application.

A soft consistency between 170 and 180 mm of runoff is recommended.

The mortar use time in optimal conditions is 90 minutes, depending on the weather.

It is recommended not to use them when it is expected that the temperatures in the setting process could exceed 40 °C or the temperature could drop below 4 °C.

STORAGE

Covered and dry rooms, avoid humidity environmental areas.

Properly stored material can be used for up to one year from the date of manufacture.

SAFETY

This product contains cement.

Avoid contact with eyes and skin, as well as inhalation of dust.

Wear protective gloves and goggles.

Keep out of the reach of children.

RESISTANCES



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat





Compressive strength following the indications of the test standard UNE EN 1015-11 at 28 days is 2.5 N / mm²

Note: The recommended water for a 175 mm runoff according to UNE EN 1.015-3, is 0.125 liters per Kg of mortar

FEATURES

Cement: Type I / 42.5 R

Sands: 0/2 mm, limestone from crushing.

Sand: 0/1 mm, limestone from crushing.

Additives: Inorganic.

QUALITY

The mortar type M-2,5 is manufactured according to the UNE EN 998-2: 2016 standard (mortars for Masonry), complying with all the parameters indicated in annex Z1 of said standard.

The test standards used to control manufactured mortars are the following:

UNE EN 1015 -1 "Granulometric Composition"

UNE EN 1015 -2 "Collection of mortar samples"

UNE EN 1015 -3 "Value of runoff by shaking table"



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat





UNE EN 1015-11 "Compression resistance value of mortars"

The data provided is based on tests carried out in our control laboratory and contrasted with laboratories accredited by the Generalitat de Catalunya.

Productos LAFAC SL guarantees that it complies with the values published in this product technical sheet.

All Mortars Manufactured by PRODUCTOS LAFAC, SL are made under the CE Conformity Certificate No.: 1170 / CDP / MR / .00076



938 69 84 19

PRODUCTOS LAFAC, S.L.
Galileo Galilei, Parc. 3
08083 CALAF (Barcelona)
Tel. 93 869 84 19
e-mail: lafac@lafac.cat

