



Natural fast cement

Product codes:

Reference: 112

Apparent density: 1,2 g/cm³ Mixing water (+/- 1): 35,00% Granulometry: < 0,08 mm

The manufacture of natural fast cement is the process of cooking natural products, without any additives, to obtain a fast-setting product.

The natural fast cement LAFAC is a product to use, however it can be used mixed with sand, useful for all types of construction applications.

The way that natural fast cement is manufactured allows us to be a product with low CO2 emissions, which leads to a better preservation of the environment.

The characteristics of natural fast cement make it the ideal product to replace plasters or limes, since higher resistance parameters are achieved and it also guarantees superior durability.

The natural fast cement LAFAC is a very useful product in all types of constructions due to its speed of setting 4 - 5 minutes









PRESENTATION

20 kg bags (aprox.)

Pallets 63 bags

USES AND APPLICATIONS

Given that the hardening time and the resistance achieved are important, the use of LAFAC NATURAL FAST CEMENT is recommended for all types of work within the trowel.

METHOD OF APPLICATION

NATURAL FAST CEMENT LAFAC is a fast hardening product so it is recommended to have the support clean and ready for the application of the product, as well as the tools necessary for its application.

CHARACTERISTICS

NATURAL FAST CEMENT LAFAC is a product of very good plasticity and great docility, thus facilitating its implementation.

Given its characteristics, it is suitable for use on any type of support (mortar, concrete, etc.)

The characteristics of the product may vary in reference to the ambient temperature at the time of its application.









* In case of temperatures above 30 °C, the use of additives that delay setting is recommended.

FEATURES HARDENED

LAFAC RAPID NATURAL CEMENT, given its characteristics, is a product whose initial resistance is in:

To obtain these resistances, the ambient temperature must not be lower than 10 $^{\rm o}{\rm C}$ and no higher than 30 $^{\rm o}{\rm C}.$

The final resistances are the following:

HANDLING

Keep out of the reach of children.

Avoid contact with eyes and skin.

Avoid inhalation

PREVENTION

If the product is sprayed dry, on the eyes or skin, wash vigorously and go to a healthcare center. Wear appropriate gloves during application. To avoid dust and splashes It is appropriate to wear safety glasses.

STORAGE

The product should be stored under cover in a clean, dry and well ventilated place.







Non-flammable product.

Consume preferably within 6 months from the date of packaging.





PRODUCTOS LAFAC, S.L. Galileo Galilei, Parc. 3 08083 CALAF (Barcelona) Tel. 93 869 84 19 e-mail: lafac@lafac.cat

