



Flexible glue cement C2TES1 Grey

Product codes:

Reference: 901

Apparent density: 1,4 g/cm³ Mixing water (+/- 1): 25,00% Granulometry: < 0,6 mm

Detachment on vertical wall: ≤ 0,5 mm

Open time after 30 m.: 30 min.

Use time: 120 min.

Adherence: ≥ 1 N/mm²

Recommended for the use of all types of stoneware with little or no absorption.

PRESENTATION

25 kg bags (approx.)

Pallets 40 bags

USES AND APPLICATIONS









Placement of tiles, ceramics, stoneware, baseboards, etc. medium and large sizes. Installation on interior and exterior supports. (* see table of coatings).

Recommended for the use of all types of stoneware with little or no absorption.

APPLICATION METHOD

Add between 25% and 28% of water and knead it well until obtaining a homogeneous paste. Wait a minimum of 10 minutes. Apply with a trowel.

The support must be completely set and clean. It must be resistant and have a plane with differences of less than 5 mm. Check with a 2 m ruler. of length.

Do not use at temperatures above 30 ° C or below 5 ° C

RECOMMENDED COATINGS

HANDLING

DRY PRODUCT:

Keep out of the reach of children. Avoid contact with eyes and skin.

Avoid inhalation

PREVENTION









In case of projection of the product dry, on eyes or skin, wash vigorously and go to a healthcare center.

Wear appropriate gloves during application. To avoid dust and splashes it is appropriate to wear safety glasses.

PERFORMANCE

Simple gluing: 4.5 (+/- 0.5) kg / m2 (10 mm. Maximum thickness)

Double gluing: 7.5 (+/- 0.5) kg / m2 (10 mm. Maximum thickness)

STORAGE

The product should be stored under cover in a clean, dry and well-ventilated place. Non-flammable product.

Consume preferably within 12 months from the date of packaging.





